

CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WEB
 WWW.CHAMAELEON-PRODUKTION.DE

TECHNICAL DATA SHEET

ACRYLIC FILLING PRIMER HS 5+1

Article number:	14881, 14882, 14883, 14884, 14885, 14886, 14887, 14888, 14889, 148880, 148890	
Intended use:	Car refinishing Product/ Filler	
General characteristics:	Chamäleon 5+1 HS Optimal is a fast-sand able 2K Compact filler with high corrosion resistance, high filling capacity and good adhesion for automotive refinishing. Also, the filling of patches (spot repair) is possible without sagging and edges margins. Coverage: $5-6 \text{ m}2/1$	
Substrate pre-treatment:		
	sand	
Application:		
Mixing ratio: Pot life:	5:1 by volume with Chamaeleon Acrylic Hardener 1-5 hours	
Application:	conventional	
	gravity-feed	
Thinners: Application viscosity:	15 - 20 % , wet on wet method 30 - 40 % 30 - 55 seconds DIN 4/20°C	
Spray nozzle:	1,4 - 1,9 mm	
Spraying pressure:	2,5 - 4,5 bar	



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WEB
 WWW.CHAMAELEON-PRODUKTION.DE

Number of coats:

1 - 3

15 min

Flash off between the coats:



Drying:

Air drying at 20°C:				
\bigcirc		120 – 180 micron	$6-8$ hours at 20° C	
Baking:				
	flash off time		10 – 15 minutes	
	drying	120 – 180 micron	30-40 minutes at 60°C	

Sanding:

grind (with sandpaper P 400 for dry or P 600 for wet sanding for one-coat finishes, for two-coat finishes use P 500 for dry and P 800 is recommended for wet sanding)

Remarks:

Process conditions: from $+ 10^{\circ}$ C and up to 75% air relative humidity. Storage: at least 3 years if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.