



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

TECHNICAL DATA SHEET

CHAMÄLEON PLASTIC PRIMER

Article number:	26014
Intended use:	Car refinishing Product/ Preparation
General characteristics:	High quality, fast drying plastic primer to treat surfaces, treated and untreated, of several types of plastic.
Product characteristics:	<ul style="list-style-type: none">• Fast drying• Excellent adhesion• Re-sprayable with all lacquer systems
Physical and Chemical	Characteristics
Contents	400 ml
Base	Polyolefine resin
Colour	Transparent
VOC-content	Approximately 99 % w/w
Solid content	Approximately 1 % w/w
Coverage	2 to 3 m ²
Re-sprayable	After 10 to 15 minutes
Usage:	Before use, carefully read the directions on the packaging and act accordingly.
Pre Treatment:	The surface should be clean, dry and free of grease. When desired, slightly sand the surface, grain 600.
Treatment:	The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

treated approximately 25 to 30 centimeter.

Apply the plastic primer in maximum two (2) thin layers.

After use:

After drying, without sanding, re-sprayable with all lacquer systems.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via:
info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.