

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A

69115 HEIDELBERG

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE WWW.CHAMAELEON-PRODUKTION.DE

TECHNICAL DATA SHEET

CHAMÄLEON FIBER GLASS FILLER

Article number:	15032, 15034, 15035, 15036, 15039

Intended use: Knife filler/ Surfacer

General characteristics:

For the filling of holes perforation corrosion, and unevennesses. The combination of the used polyester resin allows the use on all surfaces and areas, which are exposed to tension and extension. Chamaeleon Fiber Glass Polyester Putty is a 2-component polyester fibre putty as mixture of a highly reactive, amino-preaccelerated polyester resin with different mineral, environment-friendly fillers.

Fields of application:

Car sector, machine construction

Applicable on metal, wood, concrete, glass fibre

reinforced plastics

Quality and properties:

- Ease of working
- High elasticity
- Good adherence
- Very good spreadable, results in a smooth surface
- Easy to sand, even after a longer period
- Good stability, even on vertical surfaces
- No more differentiation of surfaces like zincplated, hot dip galvanized or aluminium
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt
- Free of asbestos and silicone

Technical characteristics:

Basis:
Colour:
Smell:
Chamäleon GmbH – Technical Data Sheet

polyester resin with mineral fillers green styrol



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440

FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Consistence: soft, thixotropic Pot life / Working time at 20°C: min. 12°C

Working temperature: Drying time (at 20°C, 50%

relative air humidity): Flash point:

Density at 20°C:

Addition of hardener:

Temperature resistance of the

cured material:

approx. 4 minutes

can be sanded after approx. 20-30 minutes approx. 33°C (resin); not applicable for hardener

putty 1.6 g/cm³ hardener 1.15 g/cm³

2 - 4 % (optimal mixture 2,5 %)

120°C

Application:

Before use, carefully read and observe the warning texts on the label!

- The object you wish to repair should be de-rusted, clean, dry, fat-free and sanded.
- Take the requested portion of putty compound out of the can and mix it well with the corresponding quantity of hardener.
- Apply the mixed material in the desired layer thickness.
- Clean tools immediately after use, if necessary with a nitro thinner.
- Do not return mixed material into the can.
- After approx. 20-30 minutes the repaired spot can be drilled, sanded, sawed, rasped and painted.
- Before you apply a paint coat, egalize with Chamaeleon Universal medium-grained Polyester Putty or Chamaeleon Universal Soft Polyester Putty.

Environment and labeling:

Environmentally sound: The product is 100% free of heavy metals. The

caps and packagings are made of recyclable

Disposal: Only the completely emptied cans should be put

> into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling: All Chamaeleon products comply

> with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually

valid version.





CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

Storage stability:

18 months if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%) in the unopened original container. Protect from direct sunlight, frost and humidity.

Packaging:

15032	Chamaeleon Fiber Glass Polyester Putty	250 g
15034	Chamaeleon Fiber Glass Polyester Putty	512 g
15035	Chamaeleon Fiber Glass Polyester Putty	1000 g
15036	Chamaeleon Fiber Glass Polyester Putty	1850 g
15039	Chamaeleon Fiber Glass Polyester Putty	4100 g

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.